



COLORIFICIO VENEZIANO

the Art
of
Paint

FONDO VELATURA METALLICA

Primers Line

Description

Acrylic washable hydro-painting with high coverage and resistance.

Thecnical data

- Hit preservation for 600 hours of UV-condensation according to ISO 7724.
- Chalking resistant for 600 hours of UV-condensation according to ASTM-D 659.
- Water vapor diffusion: 55 g/m² in 24 hours
- Resistance factor to vapor emission: $\mu = 2550$
- Air equivalent layer: $S_d = \mu \cdot s = 0.5 \text{ m}$ (calculated with $s = 0.2 \cdot 10^{-3} \text{ m}$).
- Coefficient of water absorption: $w = 0.08 \text{ kg}/(\text{m}^2 \cdot \text{h}^{1/2})$ aprox. — $S_d \cdot w = 0.04 \text{ kg}/(\text{m} \cdot \text{h}^{1/2})$
- Respects the theoty by Kuenzle.

Characteristics

- Specific weight: 1.410 kg/l
- Use: 150-200 g/m² per layer (0.10-0.13 l/m²)
- Result: 4-6 m²/l when the two-hand-work is over (according to the support)

High water and alkali resistance; it can be applied on any plaster or surface that has already been painted. Before use, apply one layer of **ISOEDIL A**.

Base preparation

The surface needs to be clean from dust, oil, grease, wax. Before applying the varnishing cycle, wait for 28 days after the application of the finishing plaster.

With chalked or with different absorption plasters, we suggest to apply one layer of **ISOEDIL-A** diluted with 5 parts of water or **ISOLANTE ALTA PENETRAZIONE** 1:5. We always suggest to apply this treatment also when the surface has absorption diversities.

Application

Dilution weight with water: the first layer 40%, the second 20% if with brush. Apply 2 layers waiting 4 hours at least.

The application can be done by brush or wool roll.

Supply

- Cans: 14 and 5 liters
- Colors: see the colors folder

Warnings

- Apply the material on dry and seasoned plasters.
- Do not apply during the coldest months of the year, the minimum temperature is +5 °C.

Other

FONDO VELATURA METALLICA is a washable hydro-painting for indoor use with high percentage of acrylic copolymers, selected inerts, special air and dispersing additives to improve the application, covering pigments very light resistant, anti molds, plastifiers.

FONDO VELATURA METALLICA is excellent on smooth surfaces like cement walls. The coloring used grant a long listing cromaticity.

Preservation

Avoid the preservation in very cold places.

If stocked in proper places and inside its vase it lasts 1 year.

Quality

FONDO VELATURA METALLICA is constantly and properly checked in our laboratories. The raw materials used are strictly selected and checked.

PRODUCT, TAKING UPON HIMSELF.

THE COMPANY COLORIFICIO VENEZIANO S.R.L. MAY CARRY OUT TECHNICAL ALTERATIONS ON PRODUCTS WITHOUT NOTICE.